

Production is carried out in Derbentbaşı, Çanakkale.



Result of physical analysis

Description		
Specific Weight	mg/m ³	2,72
Water absorption	%	0,4
Alkali Silica Reaction	%	0,042
Methylen Blue	MB	0,5
Flatness Index	%	7
Abrasion resistance (LA)	%	24
Abrasion resistance (MDE)	%	15
Rind ratio	%	0

Result of cemhical analysis

Content	%
CaO	55,03
Al ₂ O ₃	0,04
SiO ₂	1,59
Fe ₂ O ₃	0,03
MgO	0,02
Na ₂ O	0,01
TiO ₂	0,01
P ₂ O ₅	0,01
MnO	0,01
Ignition lost	42,91

Kepez Port

Port Features :

- ☑ Berth Lenght : 215m
- ☑ Draught : max.28m
- ☑ Ship Capacity : max.40.000 t

Loading:

- ☑ Capacity : 250 t/day (bulk material)

Akçansa Port

Port Features :

- ◆ Berth Lenght : 210m
- ◆ Ship Capacity : max.20m

Loading:

- ◆ Capacity : 360 - 500 t / shift (bulk material)